

Fast-Metal Minute Adhesive



steel-filled
 pasty and fast-curing
 gap-filling and residual elasticity

WEICON Fast-Metal Minute Adhesive is ideal for repairs and bondings with larger bonding gaps or bigger tolerances. The gap filling properties make it suitable for rough and poorly fitting surfaces but also to fill in cracks, cavities and unlevelled surfa

Fast-Metal Minute Adhesive can be used on numerous materials such as metal, plastic, fibre reinforced materials, ceramics, glass, stone and wood.

Technical data

Basis	epoxy resin, steel-filled
Nature	paste consistency, crack-filler
Supplied in	double syringe
Content	24 ml
Mixing ratio by volume (Resin/Hardener)	1 : 1
Pot life with 10 ml material at +20 °C	3-4 Min.
Density of the mixture	1,80 g/cm ³
Viscosity of the mixture at +20 °C	300.000 mPa·s
Processing temperature	+10 bis +30 °C
Curing temperature	+6 bis +40 °C
Colour	grey
Gap covering power to max.	4 mm
Handling strength (35% strength/+20 °C) after	40 Min.
Capable of bearing mechanical loads(50% strength/+20 °C) after	2 h
Final strength (100% strength/+20 °C) after	1 day(s)
Pressure	10 MPa
Tensile	24 MPa
Torsion	58 MPa
Shore hardness D	70
Steel, sand-blasted	20 N/mm ²
Aluminium, sand-blasted	19 N/mm ²
Rigid PVC, roughened	11 N/mm ²
Temperature resistance	-50 bis +145 °C

Pretreatment of the surface

To ensure a perfect bond, the surfaces to be joined must be clean and dry (e.g., clean and degrease using Cleaner S or Plastic Cleaner). Smooth surfaces should be roughened, e.g. by sandblasting.

Processing

Resin and hardener have to be mixed before use. Reject the first 5 cm of the dosed bead. Mix the product thoroughly until a homogenous colouring is achieved. Apply adhesive mixture quickly to only one of the surfaces to be bonded. Join both surfaces immediately afterwards.

The pot life given is for a material quantity of 10 ml at room temperature. If larger quantities are used, the curing time will be faster. Similarly, higher ambient temperatures shorten the cure times (as a rule of thumb, every +10 °C increase above room temperature will halve working and curing time). Temperatures below +16 °C will extend working and curing times considerably, while below about +5 °C, no reaction will take place at all.

Storage

When kept at a constant room temperature of about +20 °C and unopened in dry conditions, WEICON Epoxy Adhesives will keep for at least 18 months. Avoid direct sunlight. If these storage instructions are disregarded, the storage life will be reduced to six months.

Epoxy resins are fundamentally liable to crystallise at temperatures of less than +5 °C. This effect is accentuated by wide variations in temperature such as can frequently occur during transport in winter. This also has a negative effect on working qualities, curing and technical details, although these effects can be reversed by warming up to a maximum of +50 °C (no naked flame).

In the case of WEICON Epoxy Adhesives, careful selection and combination of the base resins (bisphenol A and F) ensures a reduction of crystallisation.

Note

Any product specifications and recommendations given herein must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do warrant the continuously high quality of our products being free from defects in accordance with and subject to our General Sales Conditions. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

Health and Safety

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

WEICON GmbH & Co. KG (Headquarter)

Königsberger Str. 255 · DE-48157 Münster
 P.O. Box 84 60 · DE-48045 Münster
 Germany

Tel. +49 (0) 251 / 93 22-0
 Fax +49 (0) 251 / 93 22-244
 Fax +49 (0) 251 / 93 22-233 Export
www.weicon.de · info@weicon.de

WEICON Middle East L.L.C.

Jebel Ali Ind Area 3 · P.O. Box 118 216
 Dubai · U.A.E

Phone +971 4 880 25 05
 Fax +971 4 880 25 09
 Mobile +971 50 545 99 83
www.weicon.ae · info@weicon.ae

WEICON Inc.

20 Steckle Place · Unit 20
 Kitchener · Ontario · N2E 2C3
 Canada

Phone +1 519 896 5252
 Fax +1 519 896 5254
 Cell +1 519 590 5168
www.weicon.ca · info@weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.

Yenibosna Mahallesi Yalçın Koreş Caddesi
 Arifağa Sokak No: 29 Kat: 3
 34530 Yenibosna – İstanbul Turkey
www.weicon.biz.tr · info@weicon.biz.tr

WEICON Romania SRL

Str. Podului Nr.1
 547176 Budiu Mic (Targu Mures)
www.weicon.com · office@weicon.com