

CA-Activator Spray



Accelerates the curing time of WEICON Contact Cyanoacrylate Adhesives.

The Activator speeds up the curing process of WEICON Cyanoacrylate Adhesives.

When applied to absorbing surfaces, like for example wood or foam etc., and all chemically-treated surfaces, like for example zinc galvanized metals etc., the Activator's effectiveness lasts approx. one minute.

With non-absorbent surfaces the Activator's effectiveness lasts up to approx. twelve hours.

Technical data

Active substance	tertiary aromatic amine
Solvent	organic solvent
Viscosity	very low
Processing temperature	+10 to +30 °C
Shelf life at room temperature	min. 12 months
Appearance	colourless, transparent

Pretreatment of the surface

Only clean and dry surfaces permit a good bonding result. Before activating the surfaces, it is necessary to clean and degrease them (e.g. with Weicon Surface Cleaner). A processing temperature of +10 to +30 °C is recommended. Before use, shake the spray can.

Processing

Apply well the Activator Spray with a spray distance of approx. 30 cm on one of the two surfaces to be bonded. Let the activator evaporate approx. 30 seconds before joining the bonding parts.

Apply the cyanoacrylate in a sufficient quantity on the non-activated surface and join the two bonding parts with pressure. A surplus of adhesive can be covered with Activator Spray and after curing it can be removed, if necessary.

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and

responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

Health and Safety

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

WEICON GmbH & Co. KG (Headquarter)

Königsberger Str. 255 · DE-48157 Münster
P.O. Box 84 60 · DE-48045 Münster
Germany

Tel. +49 (0) 251 / 93 22-0
Fax +49 (0) 251 / 93 22-244
Fax +49 (0) 251 / 93 22-233 Export
www.weicon.de · info@weicon.de

WEICON Middle East L.L.C.

Jebel Ali Ind Area 3 · P.O. Box 118 216
Dubai · U.A.E

Phone +971 4 880 25 05
Fax +971 4 880 25 09
Mobile +971 50 545 99 83
www.weicon.ae · info@weicon.ae

WEICON Inc.

20 Steckle Place · Unit 20
Kitchener · Ontario · N2E 2C3
Canada

Phone +1 519 896 5252
Fax +1 519 896 5254
Cell +1 519 590 5168
www.weicon.ca · info@weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.

Yenibosna Mahallesi Yalçın Koreş Caddesi
Arıfağa Sokak No: 29 Kat: 3
34530 Yenibosna – İstanbul Turkey
www.weicon.biz.tr · info@weicon.biz.tr

WEICON Romania SRL

Str. Podului Nr.1
547176 Budiu Mic (Targu Mures)
www.weicon.com · office@weicon.com