

Technical Datasheet

Create Date: 12.01.2016 - Page 1/1

Contact VA 5000 THIX



Cyanoacrylate Adhesive for rubber and plastics high viscosity (thixotrop) longer cure

For porous and absorbing materials and larger tolerances. Suitable for metals, plastics, and rubber, even on vertical surfaces.

Technical data

Ester type	Ethyl
Condition / nature	colourless, clear gel
Viscosity at +20°C Brookfield	ca. 25.000 mPa·s
Max. gap covering	0,2 mm
Initial adhesion on Aluminium	30 - 70 sec.
Initial adhesion on Nora test rubber	5 - 10 sec.
Initial adhesion on Rigid PVC	25 - 50 sec.
Final strength after	24 h
Temperature resistance	-50 to +90 °C

Pretreatment of the surface

To ensure a perfect bonding, the surfaces to be joined must be clean and dry (to clean and degrease use WEICON Surface Cleaner).
Smooth surfaces should be mechanically roughened.

Processing

- Apply WEICON Contact Cyanoacrylate Adhesive only on one of the surfaces to be bonded.

- The bond line should be between 0.05 mm and max. 0.2 mm (acc. to type) in thickness. Otherwise complete hardening cannot be guaranteed.

- For bonding large surfaces WEICON Contact Cyanoacrylate Adhesive should be applied drop by drop to avoid inner tensions.

- WEICON Contact Cyanoacrylate Adhesives are very economical. One drop is sufficient to cover approx. 3 - 5 $\rm cm^2$ of bonded surface.

- The parts to be joined should be bonded in an atmosphere of 40 - 80 % relative humidity. In conditions of below 40%, the cure will be considerably slowed or even inhibited. With a relative air humidity of more than 80% or with basic substrates (e.g. glass), shock-curing can occur. In such cases, some materials show a drop in bond strength of 10 - 15 %, due to inner tensions in the bond line.

- Basic-reacting surfaces (pH-value >7) will speed up the cure whereas acidic-reacting surfaces will retard and, under extreme conditions, completely inhibit the polymerization.

Storage

WEICON Contact Cyanoacrylate Adhesives should always be stored in a cool, dry and dark place. The shelf life is at least 9 months if stored at room temperature (18 - 25° C). If stored at +5°C (e.g. in a refrigerator), the shelf life can be extended to 12 months.

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

Health and Safety

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

WEICON GmbH & Co. KG (Headquarter)

WEICON Middle East L.L.C.

Königsberger Str. 255 · DE-48157 Münster Jebel P.O. Box 84 60 · DE-48045 Münster Duba Germany

 Tel.
 +49 (0) 251 / 93 22-0

 Fax
 +49 (0) 251 / 93 22-244

 Fax
 +49 (0) 251 / 93 22-233 Export

 www.weicon.de · info@weicon.de

Jebel Ali Ind Area 3 · P.O. Box 118 216 Dubai · U.A.E

Phone +971 4 880 25 05 Fax +971 4 880 25 09 Mobile +971 50 545 99 83 www.weicon.ae · info@weicon.ae

WEICON Inc.

20 Steckle Place · Unit 20 Kitchener · Ontario · N2E 2C3 Canada

Phone +1 519 896 5252 Fax +1 519 896 5254 Cell +1 519 590 5168 www.weicon.ca · info@weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.

Yenibosna Mahallesi Yalçın Koreş Caddesi Arifağa Sokak No: 29 Kat: 3 34530 Yenibosna – Istanbul Turkey www.weicon.biz.tr · info@weicon.biz.tr

WEICON Romania SRL

Str. Podului Nr.1 547176 Budiu Mic (Targu Mures) www.weicon.com · office@weicon.com