

Multi-Flex



extremely fast curing
strong adhesion
elastic

WEICON Multi-Flex is extremely fast curing, has a strong adhesion, is resistant against weathering, aging and UV. It is free from silicones and isocyanates, odorless and non-corrosive.

The 2-component adhesive and sealant based on MS-polymer is suitable for full-area and stresscompensating bondings – both indoors and outdoors.

With Multi-Flex nearly all materials, such as metal, wood, plastic, glass or ceramics, can be bonded with and among each other. It is suitable for both rough and smooth surfaces.

By using Multi-Flex, damage to the surfaces to be bonded is prevented. The bonded parts are highly loadable after curing, although the adhesive remains elastic and cushions impact loads.

The adhesive is universally applicable and can be used in many sectors of the industry, in crafts and also in household and hobby.

Technical Data

Composition	2-C-hybrid-Polymer
density	1,37 g/cm³
Viscosity adhesive	pasty
Processing temperature	+5 to +35 °C
Pot life (at +23°C and 50% rel. air humidity) *	approx. 8 Min.
Set to load bearing *	approx. 40 min.
Cure type	chemical polymerisation
Volume change (DIN 52451)	approx. 1 %

Adhesive gap bridging up to max.	10 mm
Shore A hardness (DIN 53505 / ASTM D 2240) ± 5	37
Elongation at break (DIN 53504 / ASTM D 412)	300 %
Tensile strength of pure adhesive and sealant	1,7 N/mm²
Average tensile shear strength (DIN 53283 / ASTM D 1002)	1,3 N/mm²
Temperature resistance	-40 to +90 °C

*Measured at 50% relative air humidity and +23°C

Surface pretreatment

The prerequisite for perfect adhesion are clean and dry surfaces (e.g. cleaning and degreasing with WEICON Cleaner Spray S or WEICON Plastic Cleaner). The best results are achieved when the surfaces to be bonded are mechanically roughened. The adhesive is applied only on one side.

Processing

Multi-Flex can be processed directly from the double cartridge. Reject the first centimetre of the dosed bead. Mix the product thoroughly. Apply adhesive mixture quickly to only one of the surfaces to be bonded. Join both surfaces immediately afterwards.

Storage

When unopened and stored in a normal climate (+23°C and 50 % rel. humidity), have a shelf life of 6 months.

Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Available sizes:

13362025 Multi-Flex 25 ml

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON GmbH & Co. KG
(Headquarters)
Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca
www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.
Turkey
phone +90 (0) 212 465 33 65
info@weicon.com.tr
www.weicon.com.tr

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON South East Asia Pte Ltd
Singapore
phone (+65) 6710 7671
info@weicon.com.sg

WEICON Czech Republic s.co.
Czech Republic
phone +42 (0) 417 533 013
info@weiconcz.cz

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es